

**HiFill® PA6 GF40 LE**

 Techmer Polymer Modifiers - *Polyamide 6*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Low Extractables
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.46		ASTM D792
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	1.74E+6	psi	ASTM D638
Tensile Strength (Yield)	24400	psi	ASTM D638
Tensile Strength (Break)	24200	psi	ASTM D638
Tensile Elongation (Break)	3.7	%	ASTM D638
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (0.125 in)	2.5	ft·lb/in	ASTM D256

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	500 to 580	°F
Middle Temperature	500 to 580	°F
Front Temperature	500 to 580	°F
Nozzle Temperature	500 to 580	°F
Processing (Melt) Temp	460 to 535	°F
Mold Temperature	160 to 180	°F
Injection Rate	Moderate-Fast	
Back Pressure	0.00 to 50.0	psi

