

HiFill® PA6 L N YL038MB

 Techmer Polymer Modifiers - *Polyamide 6*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Lubricant • Nucleating Agent • UV Stabilizer
Features	• Fast Molding Cycle • Lubricated • UV Resistant • Good Processability • Nucleated
Appearance	• Colors Available • Yellow
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow	0.013	in/in	ASTM D955
Water Absorption (24 hr)	2.8	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	13100	psi	ASTM D638
Tensile Elongation (Break)	70	%	ASTM D638
Flexural Modulus	410000	psi	ASTM D790
Flexural Strength	16700	psi	ASTM D790
Impact			
Notched Izod Impact (0.125 in)	0.85	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	352	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	170	°F	ASTM D648
CLTE - Flow	4.6E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	460	V/mil	ASTM D149
Flammability			
Flame Rating (0.031 in)	V-2		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
