

**InLube® PA6GF30TF13SI2**

Americhem - Polyamide 6

## General Information

**Product Description**

30% GLASS FIBER REINFORCED 13% PTFE 2% SILICONE LUBRICATED NYLON 6

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• PTFE Lubricant: 13%	• Silicone Lubricant: 2%	
Features	• Chemical Resistant • Filled • Good Dimensional Stability	• Good Mold Release • High Stiffness • High Strength	• Low Friction • Lubricated • Wear Resistant
Uses	• Closures • Consumer Applications • Electrical/Electronic Applications • Engineering Parts	• Household Goods • Industrial Applications • Industrial Parts • Office Automation Equipment	• Outdoor Applications • Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties <sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.47		ASTM D792
Specific Volume	18.8	in <sup>3</sup> /lb	
Molding Shrinkage - Flow	3.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength	17500	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Shear Strength	11000	psi	ASTM D732
<b>Impact</b>			
Notched Izod Impact (0.125 in)	1.8	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	20	ft·lb/in	ASTM D4812
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	410	°F	ASTM D648
CLTE - Flow	2.3E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Surface Resistivity	1.0E+17	ohms	
<b>Flammability</b>			
Flame Rating (0.06 in)	HB		UL 94

## Processing Information

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	480 to 550	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

