

InStruc® PA6GF30UV

Americhem - Polyamide 6

General Information

Product Description

30% GLASS FIBER REINFORCED NYLON 6 WITH UV PROTECTION

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• UV Stabilizer		
Features	• Filled • Good Dimensional Stability	• High Stiffness • High Strength	• UV Stabilized
Uses	• Automotive Applications • Closures • Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Household Goods • Industrial Applications • Industrial Parts	• Office Automation Equipment • Outdoor Applications • Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37		ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.1	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	23000	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	36000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.3	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	22	ft-lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	410	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	480 to 550	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

