

LATIGRAY 62-01 CX/25 F3

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide 6*
General Information
Product Description

Radiopaque compound based on Polyamide 6 (PA 6). Special filler. Potentially suitable for medical contact application. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Filler		
Features	• PFAS Free	• Radiopaque	• X-Ray Shielding
Uses	• Medical/Healthcare Applications		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.51	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.95 to 1.3	%	
Flow : 0.0787 in	0.90 to 1.2	%	
Water Absorption ³ (Saturation, 73°F)	1.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	421000	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	7250	psi	ISO 527-2/5
Tensile Strain (Yield, 73°F)	2.0	%	ISO 527-2/5
Tensile Strain (Break, 73°F)	15	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	7.1	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	17	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	365	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	203	°F	ISO 75-2/A
Vicat Softening Temperature	347	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	3.9E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	3.9E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
⁴	1.4	Btu·in/hr/ft ² /°F	
⁵	1.4	Btu·in/hr/ft ² /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ through plane

⁵ in plane
