

LONGLITE® PA 10G0-210S

Chang Chun Plastics Co., Ltd. (CCP Group) - Polyamide 6

General Information
Product Description

PA6 10G0-210S is an impact modified un-reinforced injection molding grade.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Impact Modifier • Mold Release		
Features	• Impact Modified		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	• Profile Extrusion
Part Marking Code (ISO 11469)	• >PA6<		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage - Across Flow	0.10 to 0.30	%	ISO 294-4
Water Absorption (Equilibrium, 73°F, 50% RH)	1.7	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	290000	psi	ISO 527-1
Tensile Stress (Break)	8700	psi	ISO 527-2
Tensile Strain (Break)	> 10	%	ISO 527-2
Flexural Modulus	290000	psi	ISO 178
Flexural Stress	11600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	9.5	ft-lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	430	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	415	°F	ISO 75-2/A
Melting Temperature ²	432	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (0.0787 in)	660	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Processing (Melt) Temp	464 to 536	°F
Mold Temperature	176 to 203	°F

Notes
¹ Typical properties: these are not to be construed as specifications.

² 10°C/min
