

LUVOTECH® eco PA6 GF50 HS BK

LEHVOSS Group - Polyamide 6

General Information

Product Description

with glass fibers, heat stabilized; black

Main Features

- Strong, stiff parts.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber		
Additive	• Heat Stabilizer		
Features	• Heat Stabilized	• High Stiffness	• High Strength
Appearance	• Black		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.18E+6	psi	ISO 527-1/1
Tensile Stress	26100	psi	ISO 527-2
Tensile Strain (Yield)	2.7	%	ISO 527-2/50
Flexural Modulus ²	1.89E+6	psi	ISO 178
Flexural Stress ³	45000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.7	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength	36	ft·lb/in ²	ISO 179/1eU
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance ⁴	> 1.0E+12	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		Internal Method

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	10 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	482 to 518	°F
Middle Temperature	518 to 554	°F
Front Temperature	536 to 572	°F
Nozzle Temperature	518 to 536	°F
Mold Temperature	158 to 230	°F

Injection Notes



During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 0.39 in/min

⁴ strip electrode R25

