

Nylene® 52GR33UV

Polymeric Resources Corporation (PRC) - *Polyamide 6*

General Information

Product Description

33% Glass Reinforced, UV Stabilized, Nylon 6

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight
Additive	• UV Stabilizer
Features	• UV Stabilized
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 73°F)	24500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength	33900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.8	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	405	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	376	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	460 to 520	°F
Middle Temperature	480 to 520	°F
Front Temperature	480 to 520	°F
Nozzle Temperature	480 to 559	°F
Processing (Melt) Temp	480 to 559	°F
Mold Temperature	81 to 160	°F
Back Pressure	50.0 to 100	psi

Notes

¹ Typical properties: these are not to be construed as specifications.

