

Plaslube® PA6 HS L MB

 Techmer Polymer Modifiers - *Polyamide 6*
General Information

General	
Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Heat Stabilizer Lubricant
Features	<ul style="list-style-type: none"> Heat Stabilized Lubricated
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.012	in/in	ASTM D955
Water Absorption (24 hr)	1.6	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11500	psi	ASTM D638
Tensile Elongation (Break)	70	%	ASTM D638
Flexural Modulus	410000	psi	ASTM D790
Flexural Strength	15700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	352	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	149	°F	ASTM D648
CLTE - Flow	4.6E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	460	V/mil	ASTM D149
Additional Information	Nominal Value	Unit	Test Method
TPCI #	7018102		

Notes
¹ Typical properties: these are not to be construed as specifications.
