

**Plaslube® PA6 GF20 RM BK**

 Techmer Polymer Modifiers - *Polyamide 6*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.28		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break)	20000	psi	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	1.00E+6	psi	ASTM D790
Flexural Strength	30000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	1.5	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	115		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	400	°F	ASTM D648
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
