

Plaslube® PA6 ML3 BK

Techmer Polymer Modifiers - *Polyamide 6*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Heat Stabilizer • Molybdenum Disulfide Lubricant: 3%
Features	• Heat Stabilized • Low Friction • Lubricated • Wear Resistant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.16		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.013	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12700	psi	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	480000	psi	ASTM D790
Flexural Strength	16300	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.31		
vs. Steel - Static	0.24		
Wear Factor	75	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.80	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	210	°F	ASTM D648
CLTE - Flow	2.6E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	480	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

