

Radilon® S RV150W 100 NAT

 Radici Group High Performance Polymers - *Polyamide 6*
General Information
Product Description

PA6 15% glass fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring improved stiffness and excellent heat ageing resistance.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Heat Stabilizer
Features	• Good Stiffness • Heat Aging Resistant • Heat Stabilized
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• GM GMW3029P-PA6-GF15H
Appearance	• Black
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-T GF15

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.23	--	g/cm ³	ISO 1183
Molding Shrinkage ²				ISO 294-4
Across Flow	1.1	--	%	
Flow	0.40	--	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	8.5	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	2.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	870000	551000	psi	ISO 527-1/1A/1
Tensile Stress (Break)	18100	10900	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	10	%	ISO 527-2/1A/5
Flexural Modulus ³	754000	--	psi	ISO 178
Flexural Stress ³	26800	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	4.8	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	24	33	ft·lb/in ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	374	--	°F	ISO 75-2/Af
Vicat Softening Temperature	401	--	°F	ISO 306/B50
Melting Temperature ⁴	428	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity ⁵	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity ⁵	1.0E+15	1.0E+13	ohms·cm	IEC 62631-3-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index (0.08 in)	1290	--	°F	IEC 60695-2-12



Processing Information

Injection	Dry Unit
Drying Temperature - Desiccant Dryer	176 °F
Drying Time - Desiccant Dryer	2.0 to 4.0 hr
Dew Point - Desiccant Dryer	< -4 °F
Suggested Max Moisture	0.15 %
Processing (Melt) Temp	464 to 536 °F
Mold Temperature	176 to 194 °F
Injection Rate	Moderate-Fast

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 280°C Melt Temperature/ 90°C Mold Temperature/ 60 MPa Cavity Pressure
- ³ 0.079 in/min
- ⁴ 10°C/min
- ⁵ 500V

