

Vydyne® B 35 GF BK EST KW2

Ascend Performance Materials Operations LLC - Polyamide 6

General Information

Product Description

Vydyne B 35 GF BK EST KW2 is standard flow, organic heat stabilized, 35% glass-fiber reinforced PA6 resin. Available in black, this product is also lubricated for improved machine feed and flow.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Additive	• Heat Stabilizer • Lubricant
Features	• Chemical Resistant • Good Flow • Heat Stabilized - Organic • Gasoline Resistant • Good Heat Resistance • Lubricated • General Purpose • Heat Stabilized
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID	• PA6-GF35

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.70	--	%	
Flow : 73°F, 0.0787 in	0.20	--	%	
Water Absorption (24 hr, 73°F)	1.9	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.6	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.57E+6	1.06E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	27300	17800	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.9	6.3	%	ISO 527-2
Flexural Modulus (73°F)	1.67E+6	1.16E+6	psi	ISO 178
Flexural Stress (73°F)	40900	25100	psi	ISO 178
Poisson's Ratio (73°F)	0.34	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°F	5.2	4.8	ft·lb/in ²	
-22°F	5.2	4.8	ft·lb/in ²	
73°F	6.2	8.1	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F	33	33	ft·lb/in ²	
-22°F	33	35	ft·lb/in ²	
73°F	38	40	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180/1A
-40°F	4.8	5.2	ft·lb/in ²	
-22°F	6.7	5.2	ft·lb/in ²	
73°F	7.1	8.6	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	424	421	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	406	392	°F	ISO 75-2/A
Melting Temperature	428	--	°F	ISO 11357-3



CLTE - Flow (73 to 131°F, 0.0787 in)	1.2E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	4.8E-5	--	in/in/°F	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (0.0394 in)	660	610	V/mil	IEC 60243-1
Comparative Tracking Index (0.118 in)	575	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.06 in	HB	--		
0.12 in	HB	--		

Processing Information

Injection	Dry Unit
Drying Temperature	176 to 194 °F
Drying Time	> 3.0 hr
Rear Temperature	446 to 536 °F
Middle Temperature	446 to 536 °F
Front Temperature	446 to 536 °F
Nozzle Temperature	446 to 536 °F
Processing (Melt) Temp	446 to 536 °F
Mold Temperature	176 to 194 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

