

AuroraGuard™ 3266G33-BK

Aurora Material Solutions, LLC - Polyamide 66

General Information

Product Description

AuroraGuard™ 3266G33-BK% is a Fiberglass Reinforced, Heat Stabilized and Lubricated Black Nylon 66 Injection Molding Grade.

Formerly branded as ENVIROLON®

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight		
Additive	• Heat Stabilizer	• Lubricant	
Features	• Heat Stabilized	• Lubricated	
Uses	• Automotive Applications		
Appearance	• Black		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Molding Shrinkage - Flow (0.118 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Water Absorption (Saturation)	0.70	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	20000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Flexural Strength	28000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.6	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	487	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	190	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.015	%
Rear Temperature	550 to 570	°F
Middle Temperature	530 to 550	°F
Front Temperature	510 to 530	°F
Nozzle Temperature	540 to 560	°F
Processing (Melt) Temp	550 to 580	°F
Mold Temperature	150 to 210	°F
Back Pressure	20.0 to 60.0	psi
Screw Speed	40 to 120	rpm

Injection Notes

Maximum Drying Time 4.0 hrs

