

**Electrafil® PA6/6 03001**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**
**General**

Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Carbon Fiber		
Additive	• Heat Stabilizer	• Impact Modifier	
Features	• Conductive	• Heat Stabilized	• High Impact Resistance
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

**Properties <sup>1</sup>**
**Physical**

	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.19		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.010	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570

**Mechanical**

	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	24000	psi	ASTM D790

**Impact**

	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	3.6	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.150 in)	19	ft-lb/in	ASTM D4812

**Hardness**

	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	111		ASTM D785

**Thermal**

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	485	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	428	°F	ASTM D648
CLTE - Flow	2.2E-5	in/in/°F	ASTM D696

**Electrical**

	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4 to 1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+4 to 1.0E+6	ohms·cm	ASTM D257

**Processing Information**
**Injection**

	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	510 to 530	°F
Middle Temperature	530 to 550	°F
Front Temperature	520 to 540	°F
Nozzle Temperature	520 to 540	°F
Processing (Melt) Temp	530 to 550	°F
Mold Temperature	175 to 220	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi

**Injection Notes**


---

Screw Speed: Medium

Recommendations for Molding and Tool Conditions: Well vented mold

Moisture Content, as received: Product is packaged at 0.2% or less.

---

### Notes

---

<sup>1</sup> Typical properties: these are not to be construed as specifications.

