

Electrafil® J-1/CF/40 NATL

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 40% Filler by Weight
Appearance	• Natural Color
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.34		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4.70E+6	psi	ASTM D638
Tensile Strength (Yield)	1.55	psi	ASTM D638
Tensile Elongation (Break)	33000	%	ASTM D638
Flexural Modulus	3.70E+6	psi	ASTM D790
Flexural Strength	38000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.4	ft-lb/in	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+6	ohms	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	510 to 540	°F
Middle Temperature	520 to 550	°F
Front Temperature	530 to 560	°F
Nozzle Temperature	540 to 570	°F
Processing (Melt) Temp	520 to 565	°F
Mold Temperature	125 to 200	°F
Injection Rate	Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow-Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

