

Electrafil® PA6/6 05002

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Filler
Features	• Conductive
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	8600	psi	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	275000	psi	ASTM D790
Flexural Strength	12000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	2.5	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	102		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	435	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	160	°F	ASTM D648
CLTE - Flow	4.4E-5	in/in/°F	ASTM D696
Electrical			
Surface Resistivity	1.0 to 1.0E+2	ohms	ASTM D257
Volume Resistivity	1.0 to 1.0E+2	ohms-cm	ASTM D257
Flammability			
Flame Rating (0.06 in)	HB		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
