

HiFill FR® PA6/6 FR 344 BK

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Heat Stabilizer • Lubricant
Features	• Flame Retardant • Heat Stabilized • Lubricated
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.27		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.018	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8100	psi	ASTM D638
Tensile Elongation (Break)	70	%	ASTM D638
Flexural Modulus	400000	psi	ASTM D790
Flexural Strength	12900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.0	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	420	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	160	°F	ASTM D648
CLTE - Flow	3.9E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	690	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.031 in	V-0		
0.08 in	5VA		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	> 6.0	hr
Rear Temperature	490 to 530	°F
Middle Temperature	490 to 530	°F
Front Temperature	490 to 530	°F
Processing (Melt) Temp	480 to 520	°F
Mold Temperature	150 to 200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm

