

HiFill® PA6/6 CC20

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.31		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.012	in/in	ASTM D955
Water Absorption (24 hr)	0.85	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	12000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	600000	psi	ASTM D790
Flexural Strength	18000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	0.80	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	485	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	410	°F	ASTM D648
Melting Temperature	490	°F	
CLTE - Flow	2.9E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	3.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	520	V/mil	ASTM D149
Flammability			
Flame Rating	HB		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
