

HiFill® PA6/6 0135 BL069

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 13% Filler by Weight
Additive	• Heat Stabilizer • Lubricant
Features	• Heat Stabilized • Lubricated
Appearance	• Blue • Colors Available • Opaque
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.35		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	1500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	700000	psi	ASTM D790
Flexural Strength	22000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.0	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	430	°F	ASTM D648
CLTE - Flow	1.8E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	490	V/mil	ASTM D149

Notes

¹ Typical properties: these are not to be construed as specifications.

