

HiFill® PA6/6 GF15 HS L WT396

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized
Appearance	• White
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.28		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3 to 9.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800000	psi	ASTM D638
Tensile Strength (Yield)	13000	psi	ASTM D638
Tensile Strength (Break)	13000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.50	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	510 to 540	°F
Middle Temperature	520 to 550	°F
Front Temperature	530 to 560	°F
Nozzle Temperature	535 to 565	°F
Processing (Melt) Temp	515 to 565	°F
Mold Temperature	150 to 225	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

