

**HiFill® PA6/6 GF25 HS L BK**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber
Additive	• Heat Stabilizer      • Lubricant
Features	• Heat Stabilized      • Lubricated
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.30		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.8	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength	24000	psi	ASTM D638
Tensile Elongation (Yield)	3.5	%	ASTM D638
Flexural Modulus	1.00E+6	psi	ASTM D790
Flexural Strength (Yield)	31000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (0.125 in)	1.6	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	115		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	482	°F	ASTM D648
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	490	V/mil	ASTM D149

**Processing Information**

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.12	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	540 to 560	°F
Processing (Melt) Temp	540 to 580	°F
Mold Temperature	130 to 200	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 100	psi

**Injection Notes**

Screw Speed: Medium  
 Recommendations for Molding and Tool Conditions: Well vented  
 Moisture Content, as received: Product is packaged at 0.2% or less.  
 Recommended Max Moisture: 0.12% down to 0.08%

