

HiFill® PA6/6 E4 HS MB

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Heat Stabilizer
Features	• Heat Stabilized • High Viscosity
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Extrusion

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.14		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.018	in/in	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	12000	psi	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	420000	psi	ASTM D790
Flexural Strength	20000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.1	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	459	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	190	°F	ASTM D648
CLTE - Flow	4.3E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	450	V/mil	ASTM D149

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.12	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	540 to 560	°F
Processing (Melt) Temp	540 to 580	°F
Mold Temperature	130 to 200	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 100	psi

Injection Notes

Screw Speed: Medium
 Recommendations for Molding and Tool Conditions: Well vented
 Moisture Content, as received: Product is packaged at 0.2% or less.
 Recommended Max Moisture: 0.12% down to 0.08%

