

**HiFill® PA6/6 GF33 5105 BK**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight
Additive	• Heat Stabilizer      • Lubricant
Features	• Heat Stabilized      • Lubricated
UL File Number	• E157319
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.40		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27000	psi	ASTM D638
Tensile Elongation (Break)	2.8	%	ASTM D638
Flexural Modulus	1.40E+6	psi	ASTM D790
Flexural Strength	39500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.0	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	480	°F	ASTM D648
Melting Temperature	504	°F	
CLTE - Flow	1.3E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	490	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
TPCI #	9829101		

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.12	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	540 to 560	°F



Processing (Melt) Temp	540 to 580 °F
Mold Temperature	130 to 200 °F
Injection Rate	Moderate-Fast
Back Pressure	50.0 to 100 psi

#### Injection Notes

Screw Speed: Medium

Recommendations for Molding and Tool Conditions: Well vented

Moisture Content, as received: Product is packaged at 0.2% or less.

Recommended Max Moisture: 0.12% down to 0.08%

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

