

HiFill® PA6/6 GF/B40 IM L

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General		
Material Status	• Commercial: Active	
Availability	• North America	
Filler / Reinforcement	• Glass Bead, 20% Filler by Weight	• Glass Fiber, 20% Filler by Weight
Additive	• Impact Modifier	• Lubricant
Features	• Lubricated	
Appearance	• Colors Available	
Forms	• Pellets	
Processing Method	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.42		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13000	psi	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	750000	psi	ASTM D790
Flexural Strength	20000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.5	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	500	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	470	°F	ASTM D648
CLTE - Flow	1.9E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	490	V/mil	ASTM D149

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.12	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	540 to 560	°F
Processing (Melt) Temp	540 to 580	°F
Mold Temperature	130 to 200	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 100	psi

Injection Notes



Screw Speed: Medium

Recommendations for Molding and Tool Conditions: Well vented

Moisture Content, as received: Product is packaged at 0.2% or less.

Recommended Max Moisture: 0.12% down to 0.08%

Notes

¹ Typical properties: these are not to be construed as specifications.

