

HiFill® PA6/6 IM L LE WT274 - EXP A

 Techmer Polymer Modifiers - *Polyamide 66*
General Information

General			
Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Impact Modifier	• Lubricant	
Features	• Impact Modified	• Low Extractables	• Lubricated
Appearance	• White		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.09		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	292000	psi	ASTM D638
Tensile Strength (Yield)	7600	psi	ASTM D638
Tensile Strength (Break)	6600	psi	ASTM D638
Tensile Elongation (Break)	52	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	14	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	4.0	hr
Rear Temperature	520 to 540	°F
Middle Temperature	520 to 540	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	520 to 540	°F
Processing (Melt) Temp	535 to 570	°F
Mold Temperature	150 to 180	°F
Injection Rate	Slow	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow-Moderate	

Notes
¹ Typical properties: these are not to be construed as specifications.
