

InElec® PA66CF20IM

Americhem - Polyamide 66

General Information

Product Description

20% CARBON FIBER REINFORCED, IMPACT MODIFIED NYLON 6/6

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight		
Additive	• Impact Modifier		
Features	• Electrically Conductive	• High Impact Resistance	• Low Temperature Toughness
	• ESD Protection	• High Stiffness	• Permanent Antistatic
	• Filled	• High Strength	
	• Good Dimensional Stability	• Impact Modified	
Uses	• Closures	• Engineering Parts	• Office Automation Equipment
	• Connectors	• Household Goods	• Outdoor Applications
	• Consumer Applications	• Industrial Applications	
	• Electrical/Electronic Applications	• Industrial Parts	
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.17		ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.80	%	ASTM D570
Mechanical			
Tensile Strength	22000	psi	ASTM D638
Tensile Elongation (Yield)	3.0 to 5.0	%	ASTM D638
Flexural Modulus	1.50E+6	psi	ASTM D790
Flexural Strength	34000	psi	ASTM D790
Impact			
Notched Izod Impact (0.125 in)	2.5	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	10	ft-lb/in	ASTM D4812
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	450	°F	ASTM D648
CLTE - Flow	2.7E-5	in/in/°F	ASTM D696
Electrical			
Surface Resistivity	1.0E+3 to 1.0E+5	ohms	ASTM D257

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	500 to 575	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

