

InLube® PA66GF30TF15

Americhem - Polyamide 66

General Information
Product Description

30% GLASS FIBER REINFORCED, 15% PTFE LUBRICATED NYLON 6/6

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• PTFE Lubricant: 15%		
Features	• Chemical Resistant	• Good Mold Release	• Low Friction
	• Filled	• High Stiffness	• Lubricated
	• Good Dimensional Stability	• High Strength	• Wear Resistant
Uses	• Closures	• Household Goods	• Outdoor Applications
	• Consumer Applications	• Industrial Applications	• Window & Door Components
	• Electrical/Electronic Applications	• Industrial Parts	
	• Engineering Parts	• Office Automation Equipment	
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.49		ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.35E+6	psi	ASTM D638
Tensile Strength	23500	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength	32500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	17	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	470	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.15 to 0.20	%
Processing (Melt) Temp	500 to 575	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

