

InStruc® PA66GF33

Americhem - Polyamide 66

General Information

Product Description

33% GLASS FIBER REINFORCED NYLON 6/6

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight		
Features	• Filled • Good Dimensional Stability	• High Stiffness • High Strength	
Uses	• Automotive Applications • Closures • Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Household Goods • Industrial Applications • Industrial Parts	• Office Automation Equipment • Outdoor Applications • Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.50E+6	psi	ASTM D638
Tensile Strength	27000	psi	ASTM D638
Tensile Elongation (Yield)	1.0 to 3.0	%	ASTM D638
Flexural Modulus	1.40E+6	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	16	ft-lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	490	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+17	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		HB	
0.13 in		HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	500 to 575	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

