

InStruc® PA66GF30HSL

Americhem - Polyamide 66

General Information

Product Description

30% GLASS FIBER REINFORCED, LUBRICATED, HEAT STABILIZED NYLON 6/6

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer	• Mold Release	
Features	• Filled • Good Dimensional Stability • Good Mold Release	• Heat Stabilized • High Stiffness • High Strength	• Lubricated
Uses	• Automotive Applications • Closures • Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Household Goods • Industrial Applications • Industrial Parts	• Office Automation Equipment • Outdoor Applications • Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.37		ASTM D792
Molding Shrinkage - Flow	3.0E-3 to 5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical			
Tensile Modulus	1.50E+6	psi	ASTM D638
Tensile Strength (Yield)	27000	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength (Yield)	33000	psi	ASTM D790
Impact			
Notched Izod Impact (0.125 in)	2.0	ft·lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	490	°F	ASTM D648
Electrical			
Surface Resistivity	> 1.0E+17	ohms	IEC 60093

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	175	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.20	%
Processing (Melt) Temp	500 to 575	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	50 to 100	rpm

