

LATAMID 66 H2 G/30

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide 66*
General Information
Product Description

Compound based on Polyamide 66 (PA 66). Improved thermal stabilisation. Glass fibres. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Features	• Good Thermal Stability	• PFAS Free	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.36	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.90 to 1.3	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Water Absorption ³ (Saturation, 73°F)	1.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-1/1
73°F	1.28E+6	psi	
140°F	899000	psi	
194°F	653000	psi	
248°F	580000	psi	
302°F	551000	psi	
Tensile Stress			ISO 527-2/5
Break, 73°F	25400	psi	
Break, 140°F	18100	psi	
Break, 194°F	15200	psi	
Break, 248°F	13800	psi	
Break, 302°F	11600	psi	
Tensile Strain			ISO 527-2/5
Break, 73°F	3.7	%	
Break, 140°F	6.2	%	
Break, 194°F	8.3	%	
Break, 248°F	9.9	%	
Break, 302°F	11	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.3	ft·lb/in ²	
73°F	4.8	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	29	ft·lb/in ²	
73°F	36	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	473	°F	ISO 75-2/A
Vicat Softening Temperature	491	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.4E-5	in/in/°F	ISO 11359-2



CLTE - Transverse (86 to 212°F)	3.1E-5 in/in/°F	ISO 11359-2
Electrical	Nominal Value Unit	Test Method
Surface Resistivity	1.0E+12 ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	530 V/mil	ASTM D149
Flammability	Nominal Value Unit	Test Method
Flame Rating		UL 94
0.030 in	HB	
0.06 in	HB	
0.12 in	HB	
Glow Wire Flammability Index		IEC 60695-2-12
0.030 in	1250 °F	
0.06 in	1250 °F	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.030 in	1290 °F	
0.06 in	1290 °F	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

