

**LATAMID 66 H2 G/25-V0KB3**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide 66*
**General Information**
**Product Description**

Compound based on Polyamide 66 (PA 66). Improved thermal stabilisation. Glass fibres. Flame retardant, UL94 V-0 class, with red phosphorous. PFAS-free product.

**General**

|                        |                        |                          |                 |
|------------------------|------------------------|--------------------------|-----------------|
| Material Status        | • Commercial: Active   |                          |                 |
| Availability           | • Africa & Middle East | • Europe                 | • North America |
|                        | • Asia Pacific         | • Latin America          |                 |
| Filler / Reinforcement | • Glass Fiber          |                          |                 |
| Additive               | • Flame Retardant      |                          |                 |
| Features               | • Flame Retardant      | • Good Thermal Stability | • PFAS Free     |

**Properties <sup>1</sup>**

| <b>Physical</b>   | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
|---|----------------------|-----------------------|--------------------|
| Density (73°F)  | 1.34                 | g/cm <sup>3</sup>     | ISO 1183           |
| Molding Shrinkage <sup>2</sup>                          |                      |                       | ISO 294-4          |
| Across Flow : 0.0787 in                                 | 0.85 to 1.1          | %                     |                    |
| Flow : 0.0787 in  | 0.30 to 0.60         | %                     |                    |
| Water Absorption <sup>3</sup> (Saturation, 73°F)        | 1.8                  | %                     | ISO 62             |
| <b>Mechanical</b>                                       | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
| Tensile Modulus (73°F)                                  | 1.16E+6              | psi                   | ISO 527-1/1        |
| Tensile Stress (Break, 73°F)                            | 18100                | psi                   | ISO 527-2/5        |
| Tensile Strain (Break, 73°F)                            | 2.8                  | %                     | ISO 527-2/5        |
| <b>Impact</b>   | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
| Charpy Notched Impact Strength                          |                      |                       | ISO 179/1eA        |
| -22°F   | 2.4                  | ft·lb/in <sup>2</sup> |                    |
| 73°F  | 3.8                  | ft·lb/in <sup>2</sup> |                    |
| Charpy Unnotched Impact Strength                        |                      |                       | ISO 179/1eU        |
| -22°F   | 19                   | ft·lb/in <sup>2</sup> |                    |
| 73°F  | 29                   | ft·lb/in <sup>2</sup> |                    |
| <b>Thermal</b>  | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
| Deflection Temperature Under Load (66 psi, Unannealed)  | 500                  | °F                    | ISO 75-2/B         |
| Deflection Temperature Under Load (264 psi, Unannealed) | 446                  | °F                    | ISO 75-2/A         |
| Vicat Softening Temperature                             | 464                  | °F                    | ISO 306/B120       |
| CLTE - Flow (86 to 212°F)                               | 1.7E-5               | in/in/°F              | ISO 11359-2        |
| CLTE - Transverse (86 to 212°F)                         | 3.3E-5               | in/in/°F              | ISO 11359-2        |
| <b>Electrical</b>                                       | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
| Surface Resistivity                                     | 1.0E+12              | ohms                  | ASTM D257          |
| Dielectric Strength                                     |                      |                       | ASTM D149          |
| 73°F, 0.0787 in, Method A (Short-Time)                  | 510                  | V/mil                 |                    |
| 73°F, 0.0787 in, Method A (Short-Time) <sup>4</sup>     | 300                  | V/mil                 |                    |
| Comparative Tracking Index <sup>5</sup> (Solution A)    | 600                  | V                     | IEC 60112          |
| <b>Flammability</b>                                     | <b>Nominal Value</b> | <b>Unit</b>           | <b>Test Method</b> |
| Flame Rating  |                      |                       | UL 94              |
| 0.030 in  | HB                   |                       |                    |
| 0.06 in   | V-0                  |                       |                    |
| 0.12 in   | V-0                  |                       |                    |
| Glow Wire Flammability Index                            |                      |                       | IEC 60695-2-12     |



|              |         |            |
|--------------|---------|------------|
| 0.04 in      | 1760 °F |            |
| 0.08 in      | 1760 °F |            |
| Oxygen Index | 28 %    | ASTM D2863 |

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air

<sup>4</sup> conditioned

<sup>5</sup> Without surfactant

