

LATISHIELD 66-13A G/30

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide 66*
General Information
Product Description

EMI shielding product based on Polyamide 66 (PA 66). Steel fibres. Glass fibres. PFAS-free product.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber • Stainless Steel Fiber
Features	• Electromagnetic Shielding (EMI) • PFAS Free

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.54	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.90 to 1.2	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Water Absorption ³ (Saturation, 73°F)	1.7	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.38E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	17400	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	2.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	24	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	500	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	473	°F	ISO 75-2/A
Vicat Softening Temperature	491	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.7E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	3.1E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	80	ohms	ASTM D257
Volume Resistivity	1.0E+2	ohms·cm	ASTM D257
Electromagnetic Reflection - Bekiscan - CP	93	%	

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air
