

LATICONTER 66 VH MI02 G/35

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide 66*
General Information
Product Description

High thermal conductivity product based on Polyamide 66 (PA 66). Glycol stabilised. Improved mechanical properties. Glass fibres. High stiffness. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Additive	• Glycol Stabilizer		
Features	• Glycol Stabilized	• PFAS Free	• Thermally Conductive

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.61	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.65 to 0.95	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Water Absorption ³ (Saturation, 73°F)	1.4	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	2.32E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	16700	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.1	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	4.8	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	473	°F	ISO 75-2/A
Vicat Softening Temperature	473	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	1.7E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- ⁴	8.3	Btu·in/hr/ft ² /°F	
-- ⁵	35	Btu·in/hr/ft ² /°F	

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ through plane

⁵ in plane
