

LEONA™ 14G20 *33E3

Asahi Kasei Corporation - Polyamide 66

General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active ¹
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 20% Filler by Weight
Additive	<ul style="list-style-type: none"> Heat Stabilizer
Features	<ul style="list-style-type: none"> Heat Stabilized
Uses	<ul style="list-style-type: none"> Automotive Applications Automotive Under the Hood Electrical/Electronic Applications Structural Parts
Appearance	<ul style="list-style-type: none"> Black
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >PA66-GF20<

Properties ²

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.10E+6	--	psi	ISO 527-1
Tensile Stress (Break, 73°F)	22200	--	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	--	%	ISO 527-2
Flexural Modulus (73°F)	1.06E+6	--	psi	ISO 178
Flexural Stress (73°F)	36300	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	4.3	--	ft·lb/in ²	ISO 179

Processing Information

Injection	Dry Unit
Drying Temperature - Vacuum Dryer	176 to 194 °F
Drying Time - Vacuum Dryer	2.0 to 3.0 hr
Processing (Melt) Temp	527 to 563 °F
Mold Temperature	167 to 185 °F

Notes
¹ All data is provisional.

² Typical properties: these are not to be construed as specifications.
