

LEONA™ 13G43

Asahi Kasei Corporation - Polyamide 66

General Information

General	
Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 43% Filler by Weight
Uses	<ul style="list-style-type: none"> Automotive Applications Automotive Under the Hood Electrical/Electronic Applications Structural Parts
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >PA66-GF43<

Properties¹

Physical	Dry	Conditioned	Unit	Test Method
Density / Specific Gravity	1.50	--		ASTM D792
Density	1.50	--	g/cm ³	ISO 1183
Molding Shrinkage				Internal Method
Across Flow	0.70	--	%	
Flow	0.30	--	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	--	1.4	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.84E+6	1.48E+6	psi	ISO 527-1
Tensile Strength	28400	22800	psi	ASTM D638
Tensile Stress (Break, 73°F)	30000	21800	psi	ISO 527-2
Tensile Elongation (Break)	3.0	4.0	%	ASTM D638
Tensile Strain (Break, 73°F)	3.0	4.5	%	ISO 527-2
Flexural Modulus	1.71E+6	1.20E+6	psi	ASTM D790
Flexural Modulus (73°F)	1.70E+6	1.26E+6	psi	ISO 178
Flexural Strength	45500	34100	psi	ASTM D790
Flexural Stress (73°F)	43900	32600	psi	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	19.0	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	5.7	8.6	ft·lb/in ²	ISO 179
Charpy Unnotched Impact Strength	40	40	ft·lb/in ²	ISO 179
Notched Izod Impact	2.4	3.9	ft·lb/in	ASTM D256
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	96	80		
R-Scale	118	--		
Rockwell Hardness				ISO 2039-2
M-Scale	96	80		
R-Scale	118	--		
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	500	--	°F	ASTM D648
Deflection Temperature Under Load (66 psi, Unannealed)	500	--	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	482	--	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	491	--	°F	ISO 75-2/A
CLTE - Flow	1.7E-5	--	in/in/°F	ASTM D696
Thermal Conductivity	2.8	--	Btu·in/hr/ft ² /°F	
Electrical	Dry	Conditioned	Unit	Test Method



Surface Resistivity	1.0E+15	--	ohms	ASTM D257
Surface Resistivity	1.0E+15	--	ohms	IEC 60093
Volume Resistivity	1.0E+15	--	ohms·cm	ASTM D257
Volume Resistivity (73°F)	1.0E+15	--	ohms·cm	IEC 60093
Dielectric Strength	760	--	V/mil	ASTM D149
Electric Strength	760	--	V/mil	IEC 60243-1
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.030 in)	HB	--		UL 94

Processing Information

Injection	Dry Unit
Drying Temperature - Vacuum Dryer	176 to 194 °F
Drying Time - Vacuum Dryer	2.0 to 3.0 hr
Processing (Melt) Temp	527 to 563 °F
Mold Temperature	167 to 185 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

