

**LUVOCOM® 1-7360/EG**

LEHVOSS Group - Polyamide 66

**General Information**
**Product Description**

with PTFE lubricant modified, high viscosity, heat stabilized; graphite grey

**Main Features**

- Improved friction and wear behaviour. Optimised for dry running operations.
- Emergency (dry) running capability.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Heat Stabilizer	• PTFE Lubricant	
Features	• Heat Stabilized	• Low Friction	• Wear Resistant
	• High Viscosity	• Lubricated	
Appearance	• Grey		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.28	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	< 10	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			DIN 16742
Across Flow	1.2 to 1.6	%	
Flow	1.5 to 3.0	%	
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	435000	psi	ISO 527-1/1
Tensile Stress	10900	psi	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	363000	psi	ISO 178
Flexural Stress <sup>3</sup>	16000	psi	ISO 178
Flexural Strain - (Yield) <sup>4</sup>	6.0	%	ISO 178
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Continuous Use Temperature <sup>5</sup>	248	°F	IEC 60216
Vicat Softening Temperature	446	°F	ISO 306/A
Service Temperature - during lifetime max. 200 hr	284	°F	
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance <sup>6</sup>	> 1.0E+12	ohms	IEC 62631-3-3

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F



Front Temperature	554 to 590 °F
Nozzle Temperature	536 to 572 °F
Processing (Melt) Temp	554 °F
Mold Temperature	194 to 248 °F

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 10 mm/min

<sup>5</sup> 20,000 hr

<sup>6</sup> strip electrode R25

