

LONGLITE® PA 21G3-202

Chang Chun Plastics Co., Ltd. (CCP Group) - Polyamide 66

General Information

Product Description

PA 21G3-202 is a flame retarded injection moulding grade.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Chemical Resistant	• Good Compressive Strength	• Wear Resistant
	• Fatigue Resistant	• Good Moldability	
	• Flame Retardant	• High Heat Resistance	
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	11600	psi	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	725000	psi	ISO 178
Flexural Stress	20300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	5.0	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	500	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	482	°F	ISO 75-2/A
Melting Temperature	509	°F	DSC
Electrical	Nominal Value	Unit	Test Method
Electric Strength (0.0787 in)	640	V/mil	IEC 60243-1
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Middle Temperature	509 to 563	°F
Nozzle Temperature	545 to 563	°F
Mold Temperature	104 to 248	°F
Injection Pressure	7110 to 17100	psi
Injection Rate	Moderate-Fast	
Holding Pressure	4270 to 11400	psi
Back Pressure	0.00 to 42.7	psi
Screw Speed	60 to 120	rpm

