

## LUVOCOM® 1-7384/EG/GY

LEHVOSS Group - Polyamide 66

### General Information

#### Product Description

with PTFE, high viscosity, heat stabilized; grey

#### Main Features

- Isotropic shrinkage characteristics.
- Improved friction and wear behaviour. Optimised for dry running operations.

#### General

|                 |                                          |                                |                  |
|-----------------|------------------------------------------|--------------------------------|------------------|
| Material Status | • Commercial: Active                     |                                |                  |
| Availability    | • Africa & Middle East<br>• Asia Pacific | • Europe<br>• Latin America    | • North America  |
| Additive        | • Heat Stabilizer                        | • PTFE Lubricant               |                  |
| Features        | • Heat Stabilized<br>• High Viscosity    | • Low Friction<br>• Lubricated | • Wear Resistant |
| Appearance      | • Grey                                   |                                |                  |

### Properties <sup>1</sup>

| Physical                                                | Nominal Value | Unit              | Test Method   |
|---------------------------------------------------------|---------------|-------------------|---------------|
| Density                                                 | 1.22          | g/cm <sup>3</sup> | ISO 1183      |
| Water Absorption (24 hr, 73°F)                          | < 1.0         | %                 | ISO 62        |
| Mechanical                                              | Nominal Value | Unit              | Test Method   |
| Tensile Modulus                                         | 435000        | psi               | ISO 527-1/1   |
| Tensile Stress                                          | 10900         | psi               | ISO 527-2     |
| Tensile Strain (Yield)                                  | 5.0           | %                 | ISO 527-2/50  |
| Flexural Modulus <sup>2</sup>                           | 363000        | psi               | ISO 178       |
| Flexural Stress <sup>3</sup>                            | 16000         | psi               | ISO 178       |
| Flexural Strain - (Yield) <sup>4</sup>                  | 6.0           | %                 | ISO 178       |
| Thermal                                                 | Nominal Value | Unit              | Test Method   |
| Deflection Temperature Under Load (264 psi, Unannealed) | 131           | °F                | ISO 75-2/A    |
| Continuous Use Temperature <sup>5</sup>                 | 230           | °F                | IEC 60216     |
| Vicat Softening Temperature                             | 464           | °F                | ISO 306/A     |
| CLTE - Flow                                             | 6.7E-5        | in/in/°F          | ISO 11359-2   |
| Service Temperature - during lifetime max. 200 hr       | 284           | °F                |               |
| Electrical                                              | Nominal Value | Unit              | Test Method   |
| Surface Resistivity                                     | > 1.0E+12     | ohms              | IEC 62631-3-2 |
| Insulation Resistance <sup>6</sup>                      | > 1.0E+12     | ohms              | IEC 62631-3-3 |

### Processing Information

| Injection          | Nominal Value | Unit |
|--------------------|---------------|------|
| Drying Temperature |               |      |
| Desiccant Dryer, A | 167           | °F   |
| Vacuum Dryer, B    | 221           | °F   |
| Drying Time        |               |      |
| Desiccant Dryer, A | 6.0 to 16     | hr   |
| Vacuum Dryer, B    | 4.0 to 6.0    | hr   |
| Rear Temperature   | 554 to 590    | °F   |
| Middle Temperature | 554 to 590    | °F   |
| Front Temperature  | 554 to 590    | °F   |
| Nozzle Temperature | 536 to 572    | °F   |



|                        |               |
|------------------------|---------------|
| Processing (Melt) Temp | 554 °F        |
| Mold Temperature       | 194 to 248 °F |

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 10 mm/min

<sup>5</sup> 20,000 hr

<sup>6</sup> strip electrode R25

