

LUVOCOM® 1-1120

LEHVOSS Group - Polyamide 66

General Information

Product Description

with PTFE lubricant modified, high viscosity; dark grey

Main Features

- Improved friction and wear behaviour. Optimised for dry running operations.
- Isotropic shrinkage characteristics.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• PTFE Lubricant		
Features	• High Viscosity • Low Friction	• Lubricated • Wear Resistant	
Appearance	• Dark Grey		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	406000	psi	ISO 527-1/1
Tensile Stress	9570	psi	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2/50
Flexural Modulus ²	363000	psi	ISO 178
Flexural Stress ³	15200	psi	ISO 178
Flexural Strain - (Yield) ⁴	6.0	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.4	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
--	52	ft·lb/in ²	
-22°F	33	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	167	°F	ISO 75-2/A
Continuous Use Temperature ⁵	230	°F	IEC 60216
Vicat Softening Temperature	446	°F	ISO 306/A
CLTE - Flow	3.3E-5	in/in/°F	ISO 11359-2
Service Temperature - during lifetime max. 200 hr	320	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance ⁶	> 1.0E+12	ohms	IEC 62631-3-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer A	6.0 to 16	hr



Vacuum Dryer, B	4.0 to 6.0 hr
Rear Temperature	554 to 590 °F
Middle Temperature	554 to 590 °F
Front Temperature	554 to 590 °F
Nozzle Temperature	536 to 572 °F
Processing (Melt) Temp	554 °F
Mold Temperature	194 to 248 °F

Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 0.39 in/min

⁴ 10 mm/min

⁵ 20,000 hr

⁶ strip electrode R25

