

**LUVOCOM® 1/GF/20/TF/10/SI/2/BK**

LEHVOSS Group - Polyamide 66

**General Information**
**Product Description**

with glass fibers, PTFE lubricant modified; black

**Main Features**

- Improved friction and wear behaviour. Optimised for dry running operations.
- Strong, stiff parts.

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Glass Fiber
Additive	• PTFE Lubricant
Features	• High Stiffness • Low Friction • High Strength • Lubricated • Wear Resistant
Appearance	• Black

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.02E+6	psi	ISO 527-1/1
Tensile Stress	21800	psi	ISO 527-2
Tensile Strain (Yield)	3.0	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	943000	psi	ISO 178
Flexural Stress <sup>3</sup>	32600	psi	ISO 178
Flexural Strain - (Yield) <sup>4</sup>	4.0	%	ISO 178
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature <sup>5</sup>	194	°F	IEC 60216
Vicat Softening Temperature	482	°F	ISO 306/A
Service Temperature - during lifetime max. 200 hr	302	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance <sup>6</sup>	> 1.0E+12	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		Internal Method

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F
Front Temperature	554 to 590	°F



Nozzle Temperature	536 to 572 °F
Processing (Melt) Temp	554 °F
Mold Temperature	194 to 248 °F

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

- <sup>1</sup> Typical properties: these are not to be construed as specifications.
- <sup>2</sup> 0.079 in/min
- <sup>3</sup> 0.39 in/min
- <sup>4</sup> 10 mm/min
- <sup>5</sup> 20,000 hr
- <sup>6</sup> strip electrode R25

