

**LUVOTECH® PA66 HS MS NT**

LEHVOSS Group - Polyamide 66

## General Information

**Product Description**

lubricant modified; natural color

## Main Features

- Emergency (dry) running capability.
- Isotropic shrinkage characteristics.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Lubricant		
Features	• Lubricated		
Appearance	• Natural Color		

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	2.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	508000	psi	ISO 527-1/1
Tensile Stress	13100	psi	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.6	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	167	°F	ISO 75-2/A
Vicat Softening Temperature	464	°F	ISO 306/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		Internal Method

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F
Front Temperature	554 to 590	°F
Nozzle Temperature	536 to 572	°F
Mold Temperature	194 to 248	°F

**Injection Notes**

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

