

**LUVOTECH® PA66 GF30 TX HS BK**

LEHVOSS Group - Polyamide 66

**General Information**
**Product Description**

with glass fibers, lubricant modified, heat stabilized; black

**Main Features**

- Improved friction and wear behaviour. Optimised for dry running operations.
- Strong, stiff parts.
- Low warpage.

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber
Additive	• Heat Stabilizer • Lubricant
Features	• Heat Stabilized • Low Friction • Wear Resistant • High Stiffness • Low Warpage • High Strength • Lubricated
Appearance	• Black

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.35	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	1.16E+6	psi	ISO 527-1/1
Tensile Stress	19600	psi	ISO 527-2
Tensile Strain (Yield)	3.0	%	ISO 527-2/50
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength	3.8	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	29	ft·lb/in <sup>2</sup>	ISO 179/1eU
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Continuous Use Temperature <sup>2</sup>	248	°F	IEC 60216
Service Temperature - during lifetime max. 200 hr	320	°F	
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance <sup>3</sup>	> 1.0E+12	ohms	IEC 62631-3-3

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F
Front Temperature	554 to 590	°F
Nozzle Temperature	536 to 572	°F
Processing (Melt) Temp	554	°F



**Injection Notes**

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 20,000 hr

<sup>3</sup> strip electrode R25

