

LUVOTECH® PA66 CF 30 HS BK

LEHVOSS Group - Polyamide 66

General Information

Product Description

with carbon fibers, heat stabilized; natural color (black)

Main Features

- Very strong and stiff parts; low coefficient of thermal expansion.
- Reduced moment of inertia compared with metal parts.
- Electrically conductive, suitable for continuous discharging of statically-generated electricity.
- High dimensionally stable precision parts with low warpage and narrow tolerance range.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber		
Additive	• Heat Stabilizer		
Features	• Electrically Conductive • Heat Stabilized • High Dimensional Stability	• High Stiffness • High Strength • Low CLTE	• Low Warpage
Appearance	• Black		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage			DIN 16742
Across Flow	0.60 to 0.80	%	
Flow	0.0 to 0.10	%	
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3.48E+6	psi	ISO 527-1/1
Tensile Stress	39200	psi	ISO 527-2
Tensile Strain (Yield)	2.0	%	ISO 527-2/50
Flexural Modulus ²	2.76E+6	psi	ISO 178
Flexural Stress ³	52200	psi	ISO 178
Flexural Strain - (Yield) ⁴	2.5	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	5.7	ft·lb/in ²	
-22°F	5.2	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	482	°F	ISO 75-2/A
Continuous Use Temperature ⁵	248	°F	IEC 60216
Vicat Softening Temperature	500	°F	ISO 306/A
CLTE - Flow	7.8E-6	in/in/°F	ISO 11359-2
Thermal Conductivity ⁶	8.3	Btu·in/hr/ft ² /°F	ISO 22007
Service Temperature - during lifetime max. 200 hr	320	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2	ohms	IEC 62631-3-2
Insulation Resistance ⁷	< 1.0E+3	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method



Flame Rating (0.06 in)	HB	Internal Method
------------------------	----	-----------------

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F
Front Temperature	554 to 590	°F
Nozzle Temperature	536 to 572	°F
Processing (Melt) Temp	554	°F
Mold Temperature	194 to 248	°F

Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 0.39 in/min

⁴ 10 mm/min

⁵ 20,000 hr

⁶ in plane; hot disk

⁷ strip electrode R25

