

Plaslube® J-1/CF/10/TF/13/Sl/2 NAT

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.25		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Flexural Strength	26000	psi	ASTM D790
Compressive Strength	20000	psi	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.60	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	475	°F	ASTM D648

