

**Plaslube® J-1/CF/10/TF/20 BK**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>		
Availability	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>Europe</li> <li>Latin America</li> </ul>	<ul style="list-style-type: none"> <li>North America</li> </ul>
RoHS Compliance	<ul style="list-style-type: none"> <li>RoHS Compliant</li> </ul>		
Forms	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.18		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength	20000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	1.00E+6	psi	ASTM D790
Flexural Strength	30000	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact	0.80	ft·lb/in	ASTM D256
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	5.5E+4	ohms	ASTM D257
Volume Resistivity	5.5E+2	ohms·cm	ASTM D257

**Additional Information**

Surface Resistivity, Techmer Test Method: 10000 to 100000 ohm  
 Volume Resistivity, Techmer Test Method: 100 to 1000 ohm-cm

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

