

**Plaslube® J-1/20/MS/5 NAT**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**
**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.52		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength	15700	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	827000	psi	ASTM D790
Compressive Strength	25000	psi	ASTM D695
<b>Impact</b>			
Notched Izod Impact	2.7	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	115		ASTM D785

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

