

Plaslube® J-1/30/TF/13/SI/2 NAT

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.49		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Mechanical			
Tensile Strength	23500	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	1.37E+6	psi	ASTM D790
Flexural Strength	35000	psi	ASTM D790
Compressive Strength	24000	psi	ASTM D695
Impact			
Notched Izod Impact	1.8	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	490	°F	ASTM D648
CLTE - Flow	2.4E-5	in/in/°F	ASTM D696
Flammability			
Flame Rating (0.06 in)	HB		UL 94

