

Plaslube® J-1/20/TF/20 BK

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	900000	psi	ASTM D790
Flexural Strength	28500	psi	ASTM D790
Compressive Strength	28000	psi	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.7	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785

