

**Plaslube® NSB 90 BK-2**

LEHVOSS Group - Polyamide 66

## General Information

**Product Description**

with PTFE; black

## Main Features

- Isotropic shrinkage characteristics.
- Improved friction and wear behaviour. Optimised for dry running operations.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• PTFE Lubricant		
Features	• Low Friction	• Lubricated	• Wear Resistant
Appearance	• Black		

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	< 1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	363000	psi	ISO 527-1/1
Tensile Stress	8700	psi	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	421000	psi	ISO 178
Flexural Stress <sup>3</sup>	13800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.8	ft·lb/in <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	203	°F	ISO 75-2/A
Continuous Use Temperature <sup>4</sup>	212	°F	IEC 60216
Vicat Softening Temperature	464	°F	ISO 306/A
CLTE - Flow	3.3E-5	in/in/°F	ISO 11359-2
Service Temperature - during lifetime max. 200 hr	284	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance <sup>5</sup>	> 1.0E+12	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		Internal Method

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	167	°F
Vacuum Dryer, B	221	°F
Drying Time		
Desiccant Dryer, A	6.0 to 16	hr
Vacuum Dryer, B	4.0 to 6.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F



Front Temperature	554 to 590 °F
Nozzle Temperature	536 to 572 °F
Processing (Melt) Temp	554 °F
Mold Temperature	194 to 248 °F

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 20,000 hr

<sup>5</sup> strip electrode R25

